

DCA

Modified Alkyd Conformal Coating (Scc3)

DESCRIPTION

DCA is a flexible, transparent and unique modified alkyd conformal coating specifically designed for the protection of electronic circuitry. It has been formulated to meet the highest defense standards in both Europe and the United States. It holds approvals including the British Ministry of Defence (MOD) DEF-STAN 59/47 Issue 4, and Underwriters Laboratories UL746E-QMJU2.

READ ENTIRE TECHNICAL BULLETIN BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- Can be cured at ambient or elevated temperatures; optimum properties achieved by heat curing
- Heat-cured coating is resistant to many solvents used within aerospace and automotive industries
- Suitable for use at temperature extremes; very wide operating temperature range
- Can be reworked using specialist removal product, Electrolube CCRG

APPROVALS

Standard	Status
RoHS Compliant (2015/863/EU)	Yes
NATO Stock Number	6850996642823 (DCA05L) 6850992530057 (DCA200H)
MIL Approval (MIL-1-46058C)	Meets Approval
IPC-CC-830	Meets Requirement
UL Approval	UL746C-QMJU2 - Meets Approval
DEF-STAN 59/47 (Issue 4)	Yes

PRODUCT INFORMATION

For available packaging sizes please visit:

electrolube.com

PHYSICAL PROPERTIES

Category	Results
Liquid Properties	
Appearance	Clear Straw/Amber
Density @ 20 °C (g/mL)	
Bulk	0.97
Aerosol	0.78
VOC Content	
Bulk	63%
Aerosol	73%
Flash Point	
Bulk	27 °C
Aerosol	<23 °C
Solid Content	
Bulk	37%
Aerosol	27%
Viscosity (mPa s @ 20 °C)	180 to 250 Bulk
Touch Dry	50 to 55 minutes
Recommended Curing Schedule*	
20 °C followed by	2 hours
90 to 120 °C	2 to 24 hours
Coverage @ 25µm	
Bulk	14.8 m ² /L
Aerosol	2.16 m ² /L (200 mL)
Dry Film Coating	
Color	Colorless

Category	Results
Operating Temperature Range (°C)	-70 to 200
Flammability	UL94 V-1
Thermal Cycling (IPC-CC-830)	Meets Approval
Coefficient of Expansion (ppm)	90
Dielectric Strength (kV/mm)	90
Dielectric Constant (1 MHz)	3.95
Insulation Resistance (DEF-STAN 59/47)	$1 \times 10^{15} \Omega$
Comparative Tracking Index	>300 Volts
Dissipation Factor @ 1MHz, 25 °C	0.037
Moisture Resistance (IPC-CC-830)	Meets Approval

APPLICATION GUIDELINES



DCA can be sprayed, dipped or brushed. The thickness of the coating depends on the method of application (typically 25 to 75 microns). Temperatures of less than 16 °C or relative humidity in excess of 75% are unsuitable for the application of DCA. As is the case for all solvent based conformal coatings, adequate extraction should be used (refer to MSDS for further information).

Substrates should be thoroughly cleaned before coating. This is required to ensure that satisfactory adhesion to the substrate is achieved. Also, all flux residues must be removed as they may become corrosive if left on the PCB. Electrolube manufacture a range of cleaning products using both hydrocarbon solvent and aqueous technology. Electrolube cleaning products produce results within Military specification.

Spraying – Bulk

DCA needs to be diluted with the appropriate thinners (DCT) before spraying. The optimum viscosity to give coating quality and thickness depends on the spray equipment and conditions, but normally a dilution ratio of 2:1 (DCA:DCT) is required. Suitable spray viscosity is typically 50-80mPa s. If bulk coating material has been agitated, allow to stand until air bubbles have dispersed. DCA is suitable both for use in manual spray guns and selective coating equipment.

The selected nozzle should enable a suitable even spray to be applied in addition to suiting the prevailing viscosity. The normal spray gun pressure required is 274 to 413 kPa (40 to 60 lb./sq.in.). After spraying, the boards should be placed in an air-circulating drying cabinet following the curing schedule highlighted on page 4/5.



Spraying - Aerosol

When applying DCA in aerosol form care must be taken to ensure the can is not shaken before use. Shaking the can will introduce excessive air bubbles and will give a poor coating finish.

The can should be held at 45°, and 200mm from the substrate to be coated. The valve should then be depressed when the can is pointing slightly off target and moved at about 100mm/s across the target. To ensure the best coating results are achieved try to use a smooth sweeping motion with small overlap for successive rows.

To ensure penetration of the coating beneath the components and in confined spaces, spray the assembly from all directions to give an even coating. After spraying, the boards should be placed in an air-circulating drying cabinet following the curing schedule highlighted on page 4/5.

TYPICAL PRODUCT APPLICATION

Dip Coating

Ensure that the coating material in the container has been agitated thoroughly and has been allowed to stand for at least 2 hours for all the air bubbles to disperse.

Conformal Coating Thinners (DCT) should be used to keep the DCA coating at a suitable viscosity for dipping (180 to 250mPa s @ 20 °C). DCT is added periodically as the solvent evaporates. The viscosity should be checked using a viscosity meter or "flow cup". The board assemblies should be immersed in the DCA dipping tank in the vertical position, or at an angle as close to the vertical as possible. Connectors should not be immersed in the liquid unless they are very carefully masked. Electrolube Peelable Coating Masks (PCM/PCS) are ideal for this application.

Leave submerged for approximately 10 seconds until the air bubbles have dispersed. The board or boards should then be withdrawn slowly (1 to 2s/mm) so that an even film covers the surface. After withdrawing, the boards should be left to drain over the tank or drip tray until the majority of residual coating has left the surface. After the draining operation is complete, the boards should be placed in an air-circulating drying cabinet following the curing schedule (shown below).

Brushing

Ensure that the coating material has been agitated thoroughly and has been allowed to settle for at least 2 hours. The coating should be kept at ambient temperature.

When the brushing operation is complete, the boards should be placed in an air-circulating drying cabinet following the curing schedule (shown below).

DRYING TIMES AND CURING CONDITIONS

The properties gained from DCA are dependent on the curing schedule employed. It is essential that the coating be allowed a minimum of two hours drying time at ambient temperature prior to any heat curing. This is necessary to allow the solvent system to evaporate.

Ambient

Ambient curing is via solvent evaporation only. Eliminating the heat curing step will reduce solvent resistance. Other properties, such as resistance to humid and corrosive environments, may also reduce but still meet the requirements of many industry standards. Coated boards should be left at room temperature for the solvent to evaporate; extraction is required in the curing area.

Commercial Most commercial users will gain satisfactory performance from this coating by curing for two hours at 90 °C after the two-hour ambient cure. This will give limited resistance to solvents.

Military If the assemblies are to be used under conditions of high temperature or be exposed to extremes of thermal cycling, the coating should be cured for 12 hours at ambient followed by 24 hours at 90 °C. For maximum solvent resistance cure at 2 hours at ambient following by 24 hours @ 120 °C. This curing schedule will give resistance to the more aggressive solvents.

It is recommended that the coating be thoroughly cured on circuits, which have design areas of very high impedance that require adjustment after application.

INSPECTION

DCA contains a UV trace, which allows inspection of the PCB after coating to ensure complete and even coverage; the stronger the reflected UV light, the thicker the coating layer is. UV light in the region of 375nm should be used for inspection.

ADDITIONAL INFORMATION

Shelf Life:

Description	Shelf Life
DCA Conformal Coating	
Aerosol	36 Months
Bulk	48 Months
Conformal Coating Thinners	36 Months
Conformal Coating Removal Gel	36 Months

SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

CONTACT INFORMATION

To confirm this document is the most recent version, please contact
TechnicalSupportTeam@hkw.co.uk
www.electrolube.com

North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460	Europe Ashby Park Coalfield Way Ashby de la Zouch Leicestershire, LE65 1JR, UK 44.01530.41960	Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100
--	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.